



B.DS.075 BW SERIES

TECHNICAL DATA SHEET



PAINTERS PRO SOFT SHEEN

GENERAL DESCRIPTION:

Fired Earth Painters Pro Soft Sheen is a luxury subtle sheen acrylic wall paint, which has been specially formulated to decorate and protect interior and exterior surfaces.

USES:

For application to suitably primed new cement plaster, concrete, fibre cement, gypsum plaster, rhinolite, brickwork and various types of building boards. May also be applied to suitably primed wood and metals.

Not suitable for direct application to gypsum or rhinolite plaster.

FEATURES & BENEFITS:

- Easy to clean
- Washable & stain resistant
- Durable protective coating
- UV & weather resistant
- Easy to apply

TECHNICAL INFORMATION	
1. PAINTERS PRO SOFT SHEEN	
PHYSICAL FORM	Non-flammable viscous liquid containing non- toxic pigments and extenders. May have a slight ammonia odour
COLOUR	White
FINISH	Smooth luxury silk finish
SPREADING RATE	Approximately 6 - 8 m ² / l per application
POLYMER TYPE	Alkali-resistant Pure Acrylic
FILLERS	Non-toxic extenders
PIGMENTS	Weather resistant types only
DRYING PROPERTIES	Surface or touch-dry: within 1 hour
RECOATING TIME	4 - 6h depending on conditions and film build
FLASH POINT	Not flammable in liquid form
PACKAGING	1L & 5L
THINNING	Not recommended, but if required to reduce viscosity add a minimum quantity of WATER. Exces- sive dilution degrades the quality of the product
CLEANING	Do not allow the product to dry on equipment. Equipment is readily cleaned using (Some deter- gent may be added to water to facilitate clean up)
APPLICATION METHOD	Supplied ready-for-use. Apply by brush, roller or airless spray. For a smoother finish on large areas use a short pile roller

DO NOT PAINT
IF THE TEMPERATURE IS BELOW 10°C OR ABOVE 35°C
IF THE SURFACE IS DAMP (MOISTURE READING ABOVE 15%)
IF IT IS RAINING OR RAIN IS FORECAST
BEFORE 9H00 AND AFTER 16H00 IN THE WINTER





B.DS.075 BW SERIES

Surface Preparation New Surfaces:

Surfaces must be thoroughly clean, dry and in sound condition before painting.

Cement plaster, concrete, fibre cement, brickwork and various types of building boards: Apply one coat of Fired Earth Painters Pro water-based Plaster Prier, followed by two coats of Fired Earth Painters Pro Soft Sheen.

Gypsum & Rhinolite Plaster: Apply one coat of solvent based plaster primer followed by two coats of Fired Earth Painters Pro Soft Sheen.

Galvanised Steel: Apply one coat of Fired Earth Metal Primer followed by one coat of Fired Earth Universal Undercoat, and two coats of Fired Earth Painters Pro Soft Sheen.

Mild Steel: Apply one coat of anti-corrosive metal primer, then apply one coat Fired Earth Universal Undercoat, followed by two coats of Fired Earth Painters Pro Soft Sheen.

Previously painted surfaces:

Thoroughly clean and prepare surface/s by removing all dirt, grease, grime and flaking paint before painting. Powdery surfaces must be sealed with one coat of Fired Earth Bonding Liquid, then apply one coat of Painters Pro Water-based Plaster Primer, followed by two coats of Painters Pro Soft Sheen. Ensure all cracks are filled with a quality acrylic crack filler prior to painting.

HEALTH & SAFETY

Keep paint away from children and animals. Never smoke, drink or eat while painting. Wear protective overalls, gloves and goggles. If accidental contact with skin should occur, wash immediately with clean water. Harmful if swallowed. Do not induce vomiting. Consult your doctor. Ensure good ventilation during application and drying. Store in a cool, dry place out of the sun.

DISCLAIMER ADVICE

The information given in this Product Information Sheet is based on controlled laboratory tests and many years of experience. It is given in good faith, but no guarantee of any performance characteristic is given or implied. Promac Paints cannot be held liable for consequential damage of whatsoever nature that may arise from the use of Promac products. Paint technology is continuously being developed and Promac Paints reserves the right to update product specifications without prior notice. Contact Promac Paints for further details.